

Table 2 – Asphalt Mixes for Binders

Item	Technical Class of the Road	Technical Category of the Street	Type and symbol of the asphalt mix ⁽¹⁾
1	I, II	I, II	Open asphalt concrete with crushed rock: - with modified bitumen, BAD 25 m ; - with bitumen, BAD 20; BAD 25
2	III	III	Open asphalt concrete with crushed rock: - with modified bitumen, BAD 25 m ; - with bitumen, BAD 20; BAD 25
			Open asphalt concrete with gravel mixed with bitumen, BAD PC 25
3	IV, V	IV, V	Open asphalt concrete with crushed rock mixed with bitumen, BAD 20; BAD 25
			Open asphalt concrete with gravel mixed with bitumen, BAD PC 25
			Open asphalt concrete with gravel sorted with bitumen BAD PS 25
⁽¹⁾ If the bitumen adhesivity on the used natural aggregates is below the 80% limit, the bitumen will be additivated with an additive that improves its adhesivity.			